


# PARTICLE SIZE DISTRIBUTION

## Typical Particle Size Distribution JETTEK® Garnet Abrasives



Grade		80	85	120
Screen Size Tyler/US	Opening Micron/Inch	Percent by Weight		
42 / 45	355 / .0139	<b>6.3</b>	<b>2.9</b>	
48 / 50	300 / .0117	<b>26.7</b>	<b>9.3</b>	
60 / 60	250 / .0098	<b>40.5</b>	<b>25.8</b>	
65 / 70	212 / .0083	<b>20.7</b>	<b>28.2</b>	<b>0.4</b>
80 / 80	180 / .0070	<b>4.3</b>	<b>21.8</b>	<b>6.6</b>
100 / 100	150 / .0059	<b>0.8</b>	<b>7.6</b>	<b>33.7</b>
115 / 120	125 / .0049		<b>3.1</b>	<b>43.2</b>
150 / 140	106 / .0041			<b>11.0</b>
170 / 170	90 / .0035			<b>3.0</b>
200 / 200	75 / .0029			<b>1.0</b>

Particle size distributions are typical. Columns may not add up to 100% due to rounding.